5

10

15

20

25

30

what is claimed is: 19

- 1. A process for upgrading a titariferous material by removal of impurities which process includes the steps of:
 - heating a titaniferous material to a temperature of less than 1300°C to produce a solid titaniferous phase and a liquid oxide or glassy phase in the presence of sufficient of compounds which encourage the formation of the liquid oxide or glassy phase;
 - phase;

 (ii) cooling the product of step (i) to form a solidified material comprising the titaniferous phase and an impurity bearing phase at a rate sufficient to ensure the susceptibility of the impurity bearing phase to leaching in either an acid or alkaline leachant; and
 - (iii) leaching the solidified material with an acidic or alkaline leachant to leach at least a portion of the impurities.
- 2. A process for upgrading a titaniferous material according to claim 1 wherein the compounds which encourage the formation of the liquid oxide or glassy phase at a temperature below 1300°C are compounds of sodium, potassium, lithium, phosphorus, silicon or boron.
 - 3. A process for upgrading a titaniferous mineral addition compound of sodium is caustic soda.
 - 4. A process for upgrading a titaniferous mineral according to Claim 2, wherein the compound of sodium is sodium carbonate.

5

00

5. A process for upgrading a titaniferous mineral addition comprises according to Claim 2, wherein the compounds include borax.

1 B

6. A process for upgrading a titaniferous mineral according to Claim 2, wherein the compounds comprise a mixture of soda ash and borax.

BU 05/10

- 7. A process according to Claim 6, wherein the titaniferous material is heated to a maximum temperature of 1000°C for a period which avoids substantial reduction to metal of contained iron oxides.
- 8. A process according to Claim 7, wherein the solidified material is leached with water.
 - 9. A process according to Claim 7, wherein the solidified material is leached with a recycled solution of leach liquor containing sodium silicate and borax to form a leachate and a residue.
 - 10. A process according to Claim 9, wherein the leachate is separated from the residue and the residue is leached with hydrochloric acid having an acid strength in a range from 1. to 20% hydrochloric acid.

25

30

20

11. A process according to claim 1 wherein the compounds include compounds which extend the effect of other compounds.

9

12. A process according to claim 11, wherein a compound which extends the effect of other compounds is borax.

00

13. A process according to claim 1 wherein sufficient odditive is compounds are present to avoid the formation of titanate

phases that are not amenable to subsequent leaching.

14. A process according to claim 1 wherein the solidified material is leached under mild conditions.

15. A process according to claim 14, wherein the solidified material is leached at atmospheric pressure.

16. An upgraded titaniferous material produced by the process of any one of claims 1 to 18.

000

, nort page